

(12) UK Patent Application (19) GB (11) 2 215 646 (13) A

(43) Date of A publication 27.09.1989

(21) Application No 8902326.1

(22) Date of filing 02.02.1989

(30) Priority data

(31) 3803687

(32) 07.02.1988

(33) DE

(71) Applicant

Emitec Gesellschaft für Emissionstechnologie mbH

(Incorporated in the Federal Republic of Germany)

**Hauptstrasse 150, D-5204 Lohmar 1,
Federal Republic of Germany**

(72) Inventor

Helmut Swars

(74) Agent and/or Address for Service

P L Drury

**Ipsley Intellectual Property Services, PO Box 55,
Ipsley House, Ipsley Church Lane, Redditch,
Worcestershire, B98 0TL, United Kingdom**

(51) INT CL⁴

B23P 17/00 // F16H 53/00

(52) UK CL (Edition J)

B3A A147

(56) Documents cited

EP 0190841 A2

(58) Field of search

UK CL (Edition J) B3A, B3J, B3Q, B3V

INT CL⁴ B21D, B23P

(54) **Assembled camshaft**

(57) An assembled camshaft comprises a one-piece or assembled tubular shaft and elements in the form of cams or bearing shells held principally by friction under constant pre-tension as a result of radial hydraulic expansion of the tubular shaft. The tubular shaft is made of a material with a yield strength of approximately 300 N/mm² and a structure that is stable up to a temperature of at least 600°C. The elements may be made of a hardenable casting material with a yield strength greater than or equal to 500 N/mm² and a minimum elongation of 1 to 2%. After joining the tubular shaft and the elements, the entire camshaft is thermochemically treated at a temperature of approximately 600°C, e.g. bath-nitrided, soft nitrided, bonderized or treated with boron, giving improved wear resistance of the cam surface. The cams may be subjected to an induction or remelting hardening process before location on the tubular shaft.

GB 2 215 646 A

ASSEMBLED CAMSHAFT

This invention relates to a process for producing an assembled camshaft comprising a one-piece or assembled tubular shaft and elements in the form of cams or bearing shells held on the shaft principally by friction locking
5 as a result of radial hydraulic expansion of the tubular shaft. The invention also relates to camshafts made by this process.

Assembled camshafts of the type described above have been undergoing development for a considerable time, but
10 the full range of demands made of volume-produced products has not yet been satisfied. The elastic properties of steel cams can be exploited to obtain a perfectly torsion-proof connection between cam and shaft, but wear resistance is not always satisfactory at high
15 loads.

In the case of cast cams, strength problems arise in conjunction with the high expansion pressures used to obtain a torsion-proof connection. Here again, enhanced wear resistance would also be desirable.

20 The present invention has the object of providing a process for producing assembled camshafts with improved wear resistance at the cam surface compared with currently available products.

The invention provides a process for producing an
25 assembled camshaft comprising a one-piece or assembled tubular shaft and elements in the form of cams or bearing shells held principally by friction locking as a result

of radial hydraulic expansion of the tubular shaft, wherein the tubular shaft material has a yield strength of approximately 300 N/mm² and a structure that is stable up to a temperature of 600°C, the elements are initially
5 fixed on the tubular shaft by hydraulic expansion, and the entire camshaft is thermochemically treated at a temperature of approximately 600°C.

In a process according to the last preceding paragraph, the tubular shaft material is chosen with a
10 yield strength of approximately or substantially 300 N/mm² or below and a structure that is stable up to a temperature of at least 600°C or above, e.g. a heat-resistant steel such as 10 Cr Mo 9 10 steel, and the elements are initially fixed on the tubular shaft by
15 hydraulic expansion and the entire camshaft is subjected to thermochemical treatment at a temperature of approximately or substantially 600°C without loss of component elasticity at the contact surfaces. In accordance with the invention, the tubular shaft
20 material, e.g. a heat-resistant steel such as 10 Cr Mo 9 10 steel, is selected specifically to permit surface treatment such as not previously used on constructed shafts of this type because the required process temperatures tended to reduce the pre-tension of the
25 fixed elements and thus release the torsion-proof connection. On the other hand, thermochemical treatment (bath nitriding, soft nitriding, bonderizing and treating with boron in particular) of the elements before fixing
30 surfaces are essential to provide a better join and prevent significant loss of strength in the friction-locking connection caused by unsuitable surfaces.

In an especially favourable further development of the process the adjacently arranged individual elements are subjected to a hardening process before location on the tubular shaft, in particular by subjecting them to an
5 induction or remelting hardening process.

The invention also provides a camshaft made according to a process in accordance with the invention, wherein the drive elements are made from a hardenable casting material with a yield strength greater than or
10 equal to 500 N/mm² and a minimum elongation of 1 to 2%. This gives especially favourable wear properties. Such elements will preferably be induction-hardened black heart castings with a martensitic structure or malleable iron castings hardened by remelting with a ledeburitic
15 structure.

CLAIMS

1. A process for producing an assembled camshaft comprising a one-piece or assembled tubular shaft and elements in the form of cams or bearing shells held principally by friction locking as a result of radial hydraulic expansion of the tubular shaft, wherein the tubular shaft material has a yield strength of approximately 300 N/mm² and a structure that is stable up to a temperature of 600°C, the elements are initially fixed on the tubular shaft by hydraulic expansion, and the entire camshaft is thermochemically treated at a temperature of approximately 600°C.
2. A process according to Claim 1, wherein the adjacently arranged individual elements are subjected to a hardening process before location on the tubular shaft.
3. A process according to Claim 2, wherein the elements are hardened in a remelting hardening process.
4. A process according to Claim 2, wherein the elements are subjected to an induction hardening process.
5. A process according to any one of Claims 1 to 4, wherein the entire camshaft is bath-nitrided.
6. A process according to any one of Claims 1 to 4, wherein the camshaft is soft-nitrided.
7. A process according to any one of Claims 1 to 4, wherein the entire camshaft is bonderized.
8. A process according to any one of Claims 1 to 4, wherein the entire camshaft is treated with boron.

9. A camshaft made according to a process according to any one of the preceding claims, wherein the drive elements are made from a hardenable casting material with a yield strength greater than or equal to 500 N/mm² and a minimum elongation of 1 to 2%.

10. A camshaft according to Claim 9, wherein the drive elements comprise induction-hardened black heart castings with a martensitic structure.

11. A camshaft according to Claim 9, wherein the drive elements comprise malleable iron castings hardened by remelting with a ledeburitic structure.

PUB-NO: GB002215646A
DOCUMENT-IDENTIFIER: GB 2215646 A
TITLE: Assembled camshaft
PUBN-DATE: September 27, 1989

INVENTOR-INFORMATION:

NAME	COUNTRY
SWARS, HELMUT	N/A

ASSIGNEE-INFORMATION:

NAME	COUNTRY
EMITEC EMISSIONSTECHNIK	DE

APPL-NO: GB08902326
APPL-DATE: February 2, 1989

PRIORITY-DATA: DE03803687A (February 7, 1988)

INT-CL (IPC): B23P017/00

EUR-CL C21D009/30 , C23C008/50 , C23C008/70 ,
(EPC): F01L001/047 , F16H053/02

US-CL-CURRENT: 74/567

ABSTRACT:

CHG DATE=19940730 STATUS=O> An assembled camshaft comprises a one-piece or assembled tubular shaft and elements in the form of cams or bearing shells held principally by friction under constant pre-tension as a result of radial hydraulic expansion of the tubular shaft. The tubular shaft is made of a material with a yield strength of approximately 300 N/mm² and a structure that is stable up to a temperature of at least 600 DEG C. The elements may be made of a hardenable casting material with a yield strength greater than or equal to 500 N/mm² and a minimum elongation of 1 to 2%. After joining the tubular shaft and the elements, the entire camshaft is thermochemically treated at a temperature of approximately 600 DEG C, e.g. bath-nitrided, soft nitrided, bonderized or treated with boron, giving improved wear resistance of the cam surface. The cams may be subjected to an induction or remelting hardening process before location on the tubular shaft.